



Technical Data Sheet

BODIOS Hydro Wax Stain No. 340

Application range	For interior use on softwoods, especially wall and ceiling panelling. Suitable for airbrush application. Not suitable for heavily used surfaces such as splash zones, floors, countertops, kitchen cabinetry, or other high-contact surfaces.														
Technical qualities	Pastel-colored, expressive, matt, aqueous, wax-containing, and polishable. Complies with German Industrial Norm DIN 53 160, fast to perspiration and saliva. Free of organic-chemical compounds in accordance with DIN EN 71, part 9.														
Full declaration	Water, mineral pigments, titanium dioxide (only in the colors 201, 125), polysaccharide, natural resin glycerol ester, beeswax soap, linseed oil, dammar, beeswax, isoaliphates, methyl cellulose, larch resin, linseed oil – stand oil, shellac, silicic acid, proteins and silver glass powder.														
Colors	<table><tr><td>002 clear</td><td>043 cherry</td><td>121 gentian</td><td>175 Danish bleached</td></tr><tr><td>023 mirabelle</td><td>107 anthracite</td><td>125 light blue</td><td>201 white</td></tr><tr><td>034 sea buckthorn</td><td>112 lime</td><td>143 apricot</td><td></td></tr></table> All colors are inter-mixable. Colors can be lightened by adding BODIOS clear No. 340 – 002! BODIOS clear can be colored with 0.5 to 3% of SUNNO Pigment Concentrate No. 425.			002 clear	043 cherry	121 gentian	175 Danish bleached	023 mirabelle	107 anthracite	125 light blue	201 white	034 sea buckthorn	112 lime	143 apricot	
002 clear	043 cherry	121 gentian	175 Danish bleached												
023 mirabelle	107 anthracite	125 light blue	201 white												
034 sea buckthorn	112 lime	143 apricot													
Dilution	Ready to use.														
Application method	Apply undiluted and sparingly, using a brush or sponge, at temperatures above 12 °C (54 °F) (see reverse side for further information).														
Coverage	1 liter (1.06 quart) is sufficient for approximately 15 - 20 m ² (161 – 215 ft ²), i.e. 57 ml/m ² . Consumption could be considerably less, depending on the condition and absorbency of the surface.														
Drying time	Drying time depends on the amount applied onto the surface, temperature, and relative humidity. Can be polished after 5 to 60 minutes and are immediately stackable afterwards.														
Cleaning	Clean equipment immediately after use with LATIS Intensive Cleaner No. 551 or TRENA pH-Neutral Cleaner No. 556 – diluted with warm water.														
Specific gravity	Approximately 1.0 g/ml.														
Safety advice	Frequent or prolonged saliva exposure, as may occur particularly with young children, is outside the intended use of the product. Under such conditions, the coating offers only limited resistance. Adult supervision and additional protection with BODIOS Protective Finish No. 344 are recommended. P102 Keep out of reach of children. P301+P310 IF SWALLOWED: rinse mouth. Do NOT induce vomiting. Immediately call a doctor.														
Disposal	According to locally regulated laws.														
Container sizes	0.5 l; 5 l; 30 l.														
Storage	Cool, dry, and frost-free. Shelf life: unopened at least 4 years. Close lid tightly after use.														
Packaging	Made of polyethylene (PE). This material is ground water neutral and recyclable.														

How to use

BODIOS Hydro Wax Stain No. 340

Preparation	The wood must be dry, solid, absorbent, finely sanded (at least 220 grain), free of resin and dust.
Application	Shake or stir product thoroughly before use. Apply sparingly and evenly in the direction of the wood grain. After 5 – 60 minutes, polish with a cotton cloth or natural brush (sisal / leather). If the coating thins out during the polishing process, reduce the polishing pressure or extend drying times. Always do a test application first. Possible defects and flaws will become visible during the polishing process. For additional protection against mechanical wear-and-tear of the surface, e.g. for furniture and toys: Apply an even and thin coat of ARDVOS-Universal Wood Oil No. 266 or KUNOS-Furniture Oil No. 245 after polishing, except for the color shades light blue (125) and lime (112), as the surface might become a bit more brownish.
Post treatment	For greater resistance, we recommend post treatment with BODIOS Protection No. 344 (protects the color - no tendency to yellowing).
Cleaning and Care	Light soiling can be removed with TRENA pH-Neutral Cleaner No. 556, diluted 1:5 with water. After-treatment by coating the entire surface with BODIOS Hydro Wax Stain No. 340.
Important tips	Especially lively and expressive effects can be created with the help of wiping techniques such as sponging, while blending different shades of BODIOS.

These directions are the result of long years of research and practical testing. They are backed by our most current expert information. New findings may invalidate this information. The latest version is available on our website at www.livos.de. This data sheet is meant to serve as information and instruction. No legal liability should be interpreted from it. In case of doubt, please contact the LIVOS customer service (see p. 1).

June 2026