

## Technical Data Sheet

## BASKO – Wood Floor Putty N° 725

Application range	Inside, for smoothing wood joints (max. 2 mm) e.g. between parquet strips. Not suitable for grouting floor boards.	
Technical qualities	Quick-drying. For smoothing with identical color, mix with grinding dust (max. 3% by weight). Easy to sand.	
Full declaration	Water, marble, diatomite, polysaccharides, quartz, mica, safflower oil, talc, Isoaliphates, casein, cellulose and natural resin ester.	
Colors	Grey white.	
Dilution	Ready for use.	
Preparation	Pre-sanding with grain size 180. Wood must be dry (moisture content below 15 %), solid, able to absorb, free of resin and dust.	
Application	Remove possible skin formed on surface and stir thoroughly. Mix BASKO –Wood Floor Putty N° 725 with about 3 % by weight grinding dust from the final grinding (grain size 120 - 150) until obtaining a homogenous, easy workable paste. Level out the entire floor area with a stainless steel spatula or a Japanese spatula. Fill out larger joints several times. When the surface is dry, sand it (grain size 150) and remove the dust.	
Coverage	Depending on the surface. Determine the exact coverage by doing a test coat.	
Cleaning	Clean equipment immediately after use with warm water and subsequently with BASKO-Thinner N° 715.	
Drying time	At 23°C (73°F) and 50% relative humidity approximately 20 minutes.	
Specific gravity	Approximately 1.19 g/ml.	
Safety advice	P102 P301+P310	Keep out of reach of children. IF SWALLOWED: Rinse mouth. Do NOT induce vomiting. Immediately call a doctor.
	After use, smooth out the Wood Floor Putty left in the tin and cover it up with foil. Close the container tightly.	
Disposal	According to locally regulated laws.	
Container sizes	0.375 kg; 2.5 kg.	
Storage	Cool, dry and frost-free. Shelf life: unopened at least 2 years.	

These directions are the result of long years of research and practical testing. They are backed by our most current expert information. New findings may invalidate this information. The latest version is available on our website at www.livos.de. This data sheet is meant to serve as information and instruction. No legal liability should be interpreted from it. In case of doubt, please contact the retailer, wholesaler, or manufacturer.

August 2016

LIVOS Plant Chemistry D-29559 Wrestedt OT Emern · Tel. +49 5825 / 88-0 · Fax 88-60 · www.livos.de · info@livos.de