



Technical Data Sheet

VARTO Shellac No. 735

Range of application	Interior windows. As a final coating of surfaces treated with BASKO paints.
Technical qualities	Low viscosity, semi-gloss, transparent. Dries very quickly, purely physical, i.e. by evaporation of the solvent. Higher water resistance in case of condensation.
Full declaration	Ethanol (grain alcohol), shellac with natural wax content, silicic acid and larch resin.
Color	Light honey colored (Gardner color index: approx. 14). Cannot be tinted.
Dilution	Ready to use.
Application method	With a brush or by spraying.
Coverage	1 l undiluted (1,06 fl. quart.) is sufficient for 12 to 16 m ² (129 to 172 ft ²) per coat, i.e. 71 ml/m ² . Test application!
Drying time	At 23 °C (74 °F) and 50 % relative humidity dry to the touch after approximately one hour. Can be painted over or sanded after approximately 24 hours. Fully hardened after 24 – 48 hours.
Cleaning up	Clean equipment immediately after use with BASKO Thinner No. 715.
Specific gravity	Approximately 0.86 g/ml.
Safety advice	<p>Ensure good ventilation during and after application.</p> <div style="display: flex; align-items: flex-start;"> <div style="margin-right: 10px;">   </div> <div> <p>H225 Highly flammable liquid and vapour. H319 Causes serious eye irritation. P210 Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking. P233 Keep container tightly closed. P243 Take precautionary measures against static discharge. P280 Wear protective gloves/protective clothing/eye protection/face protection. P370+P378 In case of fire: Use Water spray jet, Extinguishing powder, alcohol resistant foam, Carbon dioxide (CO2) to extinguish.</p> </div> </div> <p style="text-align: center;">Danger</p>
Disposal	According to locally regulated laws.
Container sizes	1 l; 2.5 l; 10 l.
Storage	Cool and dry, Shelf life: unopened at least 4 years. Close product tightly after use.
Packaging	Made of polyethylene (PE). This material is ground water neutral and recyclable. See reverse for application instructions.

How to use

VARTO Shellac No. 735

Preparation	Pre-treatment with BASKO paints. Surface must be dry, solid, clean, and free of grease and dust.
Application	A sparing, complete application (undiluted) by painting or spraying with explosion-proof equipment. (Compressed air atomizer: air pressure in bar: 3.0 – 5.0, nozzle size 0.7 – 1.0. Airless: spray pressure 50 – 120 bar, air pressure 2.0 – 3.0, nozzle size 0.007 – 0.011 inch). Don not use in direct sunlight.
Renovation coat	Clean with BASKO Thinner No. 715. Pre-sand with a fine grain, remove dust carefully. Then apply VARTO Shellac No. 735 over the entire surface, as described above.
Important tips	<p>Apply sparingly and distribute well all coating layers. Drying takes places very quickly, so you have to work quickly, otherwise there is risk of visible streaks. Color and gloss level may vary from batch to batch due to the natural raw materials.</p> <p>When spraying cover all other areas well.</p> <p>High humidity (> 65% relative humidity and temperatures < 18°C (64 °F)) can cause whitening during drying time. If this occurs, sand off and start again.</p>

These directions are the result of long years of research and practical testing. They are backed by our most current expert information. New findings may invalidate this information. The latest version is available on our website at www.livos.de. This data sheet is meant to serve as information and instruction. No legal liability should be interpreted from it. In case of doubt, please contact the retailer, wholesaler, or manufacturer.

November 2017